

Description

1K aerosol epoxy primer delivers even application, good fill, excellent corrosion protection and fast drying time.




Features & Benefits

- perfect adhesion to metal (zinc-plated, aluminium), glassware, ceramics, various plastics, wood
- to be used as a welding primer, rust protection primer
- for sand-through areas, spot repair and parts refinishing
- high filling capacity

Substrate preparation

Clean, dry, and degrease the surface with a suitable anti-silicone cleaner.

Application data

	<p>Mixing ratio</p> <p>The product is ready to use!</p> <p>Shake the can thoroughly until the mixing balls move freely (2-3 min).</p>								
	<p>Application</p> <table border="0"> <tr> <td>Number of coats</td> <td>2 coats</td> </tr> <tr> <td>Spraying distance</td> <td>10 – 15 cm</td> </tr> <tr> <td>Flash-off</td> <td>5 min</td> </tr> <tr> <td>Dry film thickness</td> <td>approx. 60 microns</td> </tr> </table> <p>After spraying turn the can upside down and spray until the valve is clean. It is strongly recommended that ready to use product is applied at temperature above 15°C/59°F.</p>	Number of coats	2 coats	Spraying distance	10 – 15 cm	Flash-off	5 min	Dry film thickness	approx. 60 microns
Number of coats	2 coats								
Spraying distance	10 – 15 cm								
Flash-off	5 min								
Dry film thickness	approx. 60 microns								
	<p>Drying (film thickness 60 µm):</p> <table border="0"> <tr> <td>Dust dry (20°C/68°F)</td> <td>15 min</td> </tr> <tr> <td>Touch dry (20°C/68°F)</td> <td>25 min</td> </tr> <tr> <td>Sanding (20°C/68°F)</td> <td>45 – 60 min</td> </tr> </table>	Dust dry (20°C/68°F)	15 min	Touch dry (20°C/68°F)	25 min	Sanding (20°C/68°F)	45 – 60 min		
Dust dry (20°C/68°F)	15 min								
Touch dry (20°C/68°F)	25 min								
Sanding (20°C/68°F)	45 – 60 min								
<p>Sanding: dry (manual P400-500, machine P400)</p> <p>Can be over coated with any solvent based or waterborne basecoats and topcoats.</p>									

2100 Epo-Prime, Epoxy Primer Spray

Ver.: 2020-5

Prod. Nr.	Description	Volume	Packaging Box
2100-0,4	Grey	400 ml	12
VOC			
VOC 2004/42/IIIB(e)(840) <840			
Shelf life			
Min. 24 months from the production date under normal storage conditions and unopened can.			
Additional Information			
FOR PROFESSIONAL USE ONLY!			
Always read the instructions.			
IMPORTANT: This product contains hazardous substances at work so it is necessary to always use/wear appropriate protective equipment. For further instructions, check the label on the product and safety data sheet. A person who uses the product for any purpose other than recommended in this technical data sheet, acts at his own risk. It is the user's responsibility to take all necessary steps to fulfil the local legislation.			
Materials described are designed for application by professional, trained personnel using proper equipment and are not intended for sale to the general public.			
Information and methods described are based on the best information and practices known to us and serve merely as guidelines for optimal use, without liability to performance, results or fitness for any intended use. We do not accept any responsibility for the behaviour of the product or damage arising from the use of the product. Before using the product, the user must check if this is the latest version.			
All products mentioned in this data sheet are trademarks owned by Silco.			